

MARMI TILES AND SLABS MARBLE AGGLOMERATE

<http://www.stoneville.co.uk/> marble - Montpellier, Nature Vive, Fusion, Mandarin Yellow, White Rock, etc. from Stoneville

Montpellier




Density: 2.45-2.55 kg/dm³
Water Absorption: <0.2%
Flexural Strength: 16-35 MPa
Abrasion Resistance: 190-390 mm³
Surface Hardness: 3-4 Mohs
Coefficient of linear thermal expansion (25°C-70°C): 10-25x10⁻⁶ m/m x °C
Slip Resistance (honed 400): R9

Nature Vive



Density: 2.45-2.55 kg/dm³
Water Absorption: <0.2%
Flexural Strength: 16-35 MPa
Abrasion Resistance: 190-390 mm³
Surface Hardness: 3-4 Mohs
Coefficient of linear thermal expansion (25°C-70°C): 10-25x10⁻⁶ m/m x °C
Slip Resistance (honed 400): R9

Albion



Density: 2.45-2.55 kg/dm³

Water Absorption: <0.2%

Flexural Strength: 16-35 MPa


Abrasion Resistance: 190-390 mm³

Surface Hardness: 3-4 Mohs

Coefficient of linear thermal expansion (25°C-70°C): 10-25x10⁻⁶ m/m x °C

Slip Resistance (honed 400): R9

Fusion



Density: 2.45-2.55 kg/dm³

Water Absorption: <0.2%

Flexural Strength: 16-35 MPa

Abrasion Resistance: 190-390 mm³

Surface Hardness: 3-4 Mohs

Coefficient of linear thermal expansion (25°C-70°C): 10-25x10⁻⁶ m/m x °C

Slip Resistance (honed 400): R9

Heritage Green



Density: 2.45-2.55 kg/dm³

Water Absorption: <0.2%

Flexural Strength: 16-35 MPa

Abrasion Resistance: 190-390 mm³

Surface Hardness: 3-4 Mohs

Coefficient of linear thermal expansion (25°C-70°C): $10-25 \times 10^{-6} \text{ m/m} \times ^\circ\text{C}$

Slip Resistance (honed 400): R9

White Rock



Density: 2.45-2.55 kg/dm³

Water Absorption: <0.2%

Flexural Strength: 16-35 MPa

Abrasion Resistance: 190-390 mm³

Surface Hardness: 3-4 Mohs

Coefficient of linear thermal expansion (25°C-70°C): $10-25 \times 10^{-6} \text{ m/m} \times ^\circ\text{C}$

Slip Resistance (honed 400): R9

Travertino Romano



Density: 2.45-2.55 kg/dm³

Water Absorption: <0.2%

Flexural Strength: 16-35 MPa

Abrasion Resistance: 190-390 mm³

Surface Hardness: 3-4 Mohs

Coefficient of linear thermal expansion (25°C-70°C): $10-25 \times 10^{-6} \text{ m/m} \times ^\circ\text{C}$

Slip Resistance (honed 400): R9

Terra Stone



Density: 2.45-2.55 kg/dm³

Water Absorption: <0.2%

Flexural Strength: 16-35 MPa


Abrasion Resistance: 190-390 mm³

Surface Hardness: 3-4 Mohs

Coefficient of linear thermal expansion (25°C-70°C): $10-25 \times 10^{-6} \text{ m/m} \times ^\circ\text{C}$

Slip Resistance (honed 400): R9

Mandarin yellow



Density: 2.45-2.55 kg/dm³

Water Absorption: <0.2%

Flexural Strength: 16-35 MPa

Abrasion Resistance: 190-390 mm³

Surface Hardness: 3-4 Mohs

Coefficient of linear thermal expansion (25°C-70°C): 10-25x10⁻⁶ m/m x °C

Slip Resistance (honed 400): R9

STONE
VILLE